



TEST REPORT

1. NO : PC19-01708E

2. Client

○ Name : Nae Woi Korea., Ltd

○ Address : #501, 9-22, Pangyo-ro 255beon-gil, Bundang-gu, Seongnam-si, Gyeonggi-do, Republic of Korea

3. Date of Test : 2019.07.02 ~ 2019.11.15

4. Use of Report : Quality Control

5. Test Sample : NWK 742S

6. Test Method

(1) ASTM G 154-16

(2) ASTM G 154-16, KS M 3026:2016

7. Test Results

1) NWK 742 White

Test Item(s)	Unit	Test Method	Test Results	Remark	Loc.
Accelerated Weathering Test(UV, 2 500 hours)-Appearance	-	(1)	No cracking, blistering	(23.0 ± 2.0) °C, (50 ± 10) % R.H.	A
Accelerated Weathering Test(UV, 2 500 hours)-Yellow Index(ΔYI)	-	(2)	5.1		

※ Accelerated Weathering Test Condition

- Lamp Type : UVA-340 nm

- Irradiance : 0.76 W/m²

- Test Cycle : UV 8h at 60 °C → Condensation 4h at 50 °C

※ Location

A : 595-10, Pyeongsin 1-ro, Daesan-eup, Seosan-si, Chungnam, 31900, Korea

----- End of Report -----

Affirmation	Tested By	Technical Manager
	Name : Kang Mee Jeong	Name : Shin Jin Yong

This report is not accredited by KOLAS.

Our report apply only to the standards or procedures identified and to the sample(s) tested unless otherwise specified. The test results are not indicative of representative of the qualities of the lot from which the sample was taken or of apparently identical or similar products. The results of using only a portion of this report cannot be guaranteed. The authenticity of this test report can be checked on KCL website(www.kcl.re.kr).

2019.11.15

Korea Conformity Laboratories

President Yoon, Kap Seok *kapseok*

Result Inquiry : 252-7, Techno 2-ro, Yuseong-Gu, Daejeon, Korea (82-42-723-3074)

